

SELECTION & SPECIFICATION DATA

Type	Fast Drying Asphalt Cutback
Description	Blackhawk 5157 Chassis Black is a coating that can be used for many purposes. This product has good corrosion and weather proof features. It also has excellent coverage and adhesion to marginly prepared surfaces. It is widely used to protect steel beams, steel pipes, and other metal parts. It also functions well as a primer. Blackhawk 5157 Chassis Black has a very high solids content giving excellent coverage. It is supplied in the correct consistency for application and needs no thinning if kept air tight between uses.
Uses	Corrosion protection of: <ul style="list-style-type: none"> • Steel beams • Steel pipes • Engine chassis' Acts as an excellent primer for metal substrates.
Color	Black
Primer	Self-priming
Topcoat	Consult ErgonArmor
Finish	Gloss
Dry Film Thickness (DFT)	3 - 5 mils
Solids Content	55% ± 5% by weight
VOC Value(s)	<450g/L, 3.75 lbs/gal

SUBSTRATES & SURFACE PREPARATION

All	All surfaces must be clean and free from debris and loose scale material or anything that may interfere with adhesion or act as a bond breaker with the desired substrate.
------------	--

MIXING & THINNING

Mixing	No mixing required. Ready to use as is.
---------------	---

Thinning Do not thin

Cleanup Mineral spirits

APPLICATION GUIDELINES

Airless Spray Single Leg or Pot Pump size 15:1 or greater
Hose length: 20 ft x 1/2-inch ID

Brush Apply with a wide fiber brush in order to create a smooth uniform film.

Roller Use a low nap phenolic core roller.

PACKAGING, HANDLING & STORAGE

ITEM#	PACKAGING
K-5164-005-001-CB	Pail - 4.7 gallons
K-5164-053-001-CB	Drum - 53 gallons
K-5164-350-001-CB	Tote - 340 gallons

Theoretical Coverage Rate 220 square feet per gallon at 4 mils DFT

Storage & Shelf Life Estimated shelf life is 12 months when stored in a dry area at 75°F (24°C). Actual shelf life may vary with storage conditions. Do not store below 40°F (4°C) or above 110°F (43°C). Store indoors. This product is not affected by excursions below these published storage temperatures, down to 10°F (-12°C), for a duration of no more than 14 days. Always inspect the product prior to use to make sure it is smooth and homogeneous and properly mixed.

SAFETY

Safety Read and follow all caution statements on this product data sheet and on the SDS for this product. Wear protective clothing, gloves and eye protection.

Ventilation Thorough air circulation must be used during and after application until the product is cured. User should test and monitor exposure levels to ensure all personnel are within safe limits. Consult product SDS for further information.

Rev. 03/2025

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.